

Advanced Propellant/Additive Development for Fire Suppressing Systems

Stephen Fallis and Russell Reed

Research Department, Naval Air Warfare Center Weapons
Division, China Lake, CA

Paul Wierenga, Gary F. Holland

Aerojet-Redmond Rocket Center
Redmond, WA

Halon Options Technical Working Conference

May 2003

Outline of Presentation



- **Introduction**
 - Program Background Information
 - Fire Suppression and GG's
- **Propellant Development**
 - Cooler, High Nitrogen Compositions
- **Effectiveness Testing**
 - SPFEs (Solid Propellant Fire Extinguishers)
 - HFEs (Hybrid Fire Extinguishers)
- **Summary**
- **Acknowledgements**

**GF Holland
PH Wierenga**

**S Fallis
R Reed**



**Olin Aerospace
Rocket Research**

$$FE = X_{\text{dil}} + X_{\text{cool}} + X_{\text{chem}} + X_{\text{flow}}$$

- $X_{\text{dil}} \sim$ dilution effects: $[O_2] \approx 12\text{-}13\%$
- $X_{\text{cool}} \sim$ cooling effects: $C_p \approx 40\text{-}50 \text{ cal/}^\circ\text{K-mol } O_2$
- $X_{\text{chem}} \sim$ chemical effects: radical traps
- $X_{\text{flow}} \sim$ flow rate effects: dec τ_{res} in flame zone

Solid Propellant Fire Suppression Systems



Current State of the Art:

- Size competitive w/ Halon-1301 (volume, mass)
- Effective, clean, fast acting
- Environmentally rugged and reliable
- Low human hazard: CO₂, N₂, H₂O
- Environmentally friendly, SNAP-approved
- Temperature compensating designs
- All based on commercial automotive airbag technology

Next Generation Objectives:

Improve effectiveness via:

- Increased cooling
 - Cooler burning propellants
 - Hybrid configurations
- Increased gas output
- Added chemical activity

Opportunity:

- 2-5x reduction in agent loads




Program Background Information: Propellant Development




- **Phase I**
 - Developmental Compositions, High-N Compounds
 - Chemically Active Formulations: vary agent
- **Phase II**
 - BTATZ Scale-up
 - Chemical additives incorporated into SPFE, HFE
- **Phase III**
 - BTATZ Formulations: Ballistic Testing
 - Chemically Active Formulations: vary [agent]

High-Nitrogen Fuels Used in CL/PAC Propellant Development


AEROJET




Triaminoguanidinium
Nitrate (TAGN)



Bis(aminotetrazolyl)tetrazine
(BTATZ)



5-Aminotetrazole
(5AT)



Bitetrazole (BT)

Effect of Combustion Temperature on Ballistics

AEROJET




- Trends

- BR not predictable by T_c alone
- Falloff in BR follows Arrhenius-type activated process

- $\ln(BR) = f(1/T_c)$
- Slopes vary

- Predictive tool?



Control of Exhaust Temperatures



- **Propellant modifications**

- Vary F, O





- Incorporate coolant

- Calculate T_c (combustion)


- $T_{meas} \sim 200\text{--}600\text{ }^\circ\text{C}$

- **Hybrid combinations**

- $T_{meas} \sim 50\text{ } 100\text{ }^\circ\text{C}$



5-Aminotetrazole
(5AT)



Bis(aminotetrazolyl)tetrazine
(BTATZ)


Developmental Propellants: High Gas, Cooler Gas

AEROJET




Descriptors	T _c , °C	Gas, mol/100g	theoretical density, g/cc	BR ₁₀₀₀ , in/s
BTSN-00	2501	2.27	2.38	1.09
BTSN-10Ê	2289	2.12	2.43	TBD
BTSN-20	2032	2.00	2.49	0.75
BTSN-30	1621	1.89	2.55	TBD
BTSN-40	1537	1.79	2.61	0.35
BTSN-50	1071	1.54	2.67	0.15

Propellant Combustion



Aerojet Fire Test Fixture



Test Fixture Parameters




- ~700 kW Flame Intensity
 - Flame temperature = ~1000 K (1300 °F)
 - Air flow rate = 450 g/s (1 lb_m/s)
 - Fuel flow rate = 15 g/s (0.033 lb_m/s)
 - Air:fuel ratio = 31
 - Equivalence ratio = 0.5
- 24 ft³ Total Volume (16 ft³ fire zone)
 - Residence time = ~1 s (through fire zone)
- 100-200 ms Discharge Time for SPFEs and HFEs

$$\dot{m}_{air} / \dot{m}_{fuel}$$

Aerojet SPFE Active Agent Test Unit

AEROJET



Test Videos: Active Agent Assessment

AEROJET




$\text{Fe}_2\text{O}_3/\text{FeCp}_2$

$\text{KI}/\text{K}_2\text{CO}_3$

Summary of FTF Data




	50% split				50% split		
Neat agent	Agent mass, g	Test No.	Result	Neat agent	Agent mass, g	Test No.	Result
<i>KI</i>	20	027-06	fire not out	<i>Fe₂O₃</i>	40	038-01	fire not out
	40	027-07	fire not out		80	038-02	fire not out
	40	027-05	fire out				
	60	027-04	fire out				
<i>KBr</i>	40	032-02	fire not out	<i>Ferrocene</i>	40	039-01	fire not out
	60	032-03	fire not out		80	039-02r	fire not out
	60	032-01	fire not out				
<i>K₂CO₃</i>	20	035-03	fire not out	<i>Fe Oxalate</i>	40	040-01	fire not out
	40	035-02r	fire out				
	60	035-01	fire out	<i>PBPE</i>	60	041-01	fire not out



- **Advantages**
 - Rapid discharge
 - No storage pressure
 - T-compensating
- **Applications**
 - Ballistic & safety fire protection for aircraft.
 - Land vehicle engine compartments.
 - Electronics bays

Hybrid Fire Extinguishers




- **Advantages**

- Tailorable discharge
- Fits into current Halon 1301 envelope
- Low/No storage pressure
- T-compensating discharge

- **Applications**

- Armored vehicle engine & crew compartments.
- Aircraft engine nacelles.
- Automotive & industrial fire/explosion protection





Fire Test, active agent



Discharge demo,
active agent (100x)

3304/FM200 HFE Fire Out Sequence



HFE Function: T= 0 msec



T= 33 msec



T= 66 msec



T= 99 msec




T= 132 msec



T=165 msec

Performance Summary



Conclusions



- **BTATZ-based formulations provide excellent platform for cooler-burning FS compositions**
- **Increasing the amount of active additive leads to more efficient SPFE and HFE performance.**
 - **Catalysis not yet saturated**
- **HFE's effective for low vapor pressure fluids**
 - **Higher-boiling fluorocarbons**
 - **Water-based systems**



- **Suppression and Ballistics Testing:**
 - At China Lake: Dr. T. P. Parr, R. Stalnaker, J. Hitner, P. Curran, A.I. Atwood
 - At Aerojet/GD: Gary Gregg, Jennifer McCormick, Chuck Anderson, Ron Paxton, Ray Nikko

- **Funding**
 - SERDP's Next Generation Fire Suppression Technology Program (NGP)
 - Naval Air Combat Survivability Program